



*"It's What the Pros Use"*

## Technical Product Data

### RP 1.1 Epoxy Primer

#### Basic Uses & Description:

RP 1.1 Epoxy Primer is a black, single-component epoxy primer. It incorporates state of the art water based technology to produce an extremely versatile product that penetrates and seals porous substrates. It is effective at increasing the bond of silicone topcoats to a variety of surfaces. It will also help to "solidify" punky or chalky surfaces. RP 1.1 Epoxy Primer is safe to use, has a very little odor, and is easy to clean. RP 1.1 Epoxy Primer is designed to penetrate and seal porous substrates to improve the adhesion of PM Home Sil High Solids Silicone Roof Coatings. It develops a tenacious bond to concrete, wood, fiberglass, steel, galvanized and aluminum surfaces. Although RP 1.1 Epoxy Primer will greatly enhance the adhesion of various topcoats over metal surfaces, it is not designed to add to the corrosion resistance of the system, beyond what the topcoat provides.

#### Advantages:

- 1. Adhesion:** Penetrates and "wets" into porous surfaces, imparting a tenacious chemical and physical bond between the substrate and topcoat. It is also effective over damp concrete or wood surfaces.
- 2. Non-Dusting:** Penetrates deeply to eliminate concrete dusting, providing for easy cleanup and minimum maintenance.
- 3. Deep Penetration:** Its low viscosity allows RP 1.1 Epoxy Primer to penetrate into and preserve dense surfaces such as smooth troweled concrete floors, oriented strandboard, fiberglass and various types of metal surfaces.
- 4. Anti-Spalling:** Applied to concrete decks, walkways, industrial areas, etc., RP 1.1 Epoxy Primer will effectively protect against the intrusion of destructive salts, oils, solvents and gasoline. It also prevents spalling and pit-ting caused by freeze/thaw cycling.

#### Application:

RP 1.1 Epoxy Primer may be applied by brush, roller or by airless spray equipment. Airless spray equipment is the preferred method. Any airless spray equipment capable of 1,000 psi (6,980 kpa) and 1/2 gallon per minute (1.9 l/minute) delivery can be used. A reversible, self-cleaning spray tip with an orifice size of .015" to .027" (.4 mm to .7 mm) and a minimum 40-degree fan angle is recommended. Before spraying, flush equipment with clean water to prevent contamination. Coverage rate will vary depending upon surface porosity. One coat is usually sufficient for sealing substrates when RP 1.1 Epoxy Primer is used as a primer. When used as a sealer/finish, two coats are required to achieve a uniform sheen. Two coats may also be required when sealing lightweight concrete or other highly porous surfaces. The following are approximate application rates:

**Lightweight Concrete:** 100 to 150 sq.ft./gal. (2.4 - 3.7 m<sup>2</sup>/l)

**Wood:** 300 sq. ft./gallon (7.3 m<sup>2</sup>/l)

**Fiberglass:** 300 to 400 sq. ft./gallon (7.3- 9.8 m<sup>2</sup>/l)

**Metal:** 300 to 400 sq. ft./gallon (7.3 - 9.8 m<sup>2</sup>/l)

Thin as necessary with water to achieve adequate penetration of the surface being sealed. When used as a sealer/finish apply a second coat of RP 1.1 Epoxy Primer at approximately 50% greater coverage rate than those listed above. When used as a primer on exterior applications, RP 1.1 Epoxy Primer should be top coated within 48 hours to ensure optimum bonding characteristics. Do not permit RP 1.1 Epoxy Primer to puddle or "glaze" over on top of the substrate. Allow to thoroughly dry prior



*"It's What the Pros Use"*

## Technical Product Data

to applying top coat. Do not allow RP 1.1 Epoxy Primer to be exposed for more than FIVE (5) days. If RP 1.1 Epoxy Primer is exposed for more than FIVE (5) days, reapply RP 1.1 Epoxy Primer to the substrate to achieve optimal adhesion.

### Surface Preparation:

All surfaces must be clean and free of any dirt, oil, grease, soapy films, surface chemicals or other foreign contaminants. Slightly damp surfaces will not affect the performance of RP 1.1 Epoxy Primer, provided there is no standing water or frost. New concrete should be water-cured in lieu of using a curing compound. Any form of curing compound or release agent on any surface to be sealed with RP 1.1 Epoxy Primer must be completely removed, along with any laitance. Prior to applying P-110, all loose material, dirt and dust must be removed by use of a power vacuum, stiff-bristled broom or compressed air. If concrete is badly spalled, restore surface to a reasonable condition using cementitious patching or resurfacing compound. Fiberglass surfaces should be scuff-sanded prior to priming. Metal surfaces must be free of oily residue and loose rust. Previously painted surfaces should be brush blasted or mechanically abraded to remove the existing finish.

Existing concrete must be cleaned using biodegradable chemical cleaner and water. Cleaning shall be accomplished using mechanical scrubbers. Rinse thoroughly with fresh water to remove all traces of the chemical cleaner. If general cleaning is not adequate, then surfaces should be cleaned and etched as recommended for new concrete.

If surfaces are highly contaminated, or if surfaces are to be subjected to unusual service conditions, consult Progressive Materials, LLC Technical Service Department for recommendations.

### Limitations & Precautions

RP 1.1 Epoxy Primer is a thin penetrating sealer. It is not designed for use as a high-build surface coating. Do not use over metal under immersion conditions. RP 1.1 Epoxy Primer will freeze and become unusable below 32°F (0°C). Do not ship or store unless protection from freezing is available. Do not apply if conditions will not permit complete cure before rain, dew or freezing temperatures occur. Do not apply in the late afternoon if moisture condensation can appear during the night. Do not apply RP 1.1 Epoxy Primer at temperatures below 50°F (10°C). RP 1.1 Epoxy Primer may be an irritant to skin. Avoid breathing of vapor or spray mist. Approved MSHA/NIOSH chemical cartridge respirator must be worn by applicator. Avoid contact with eyes and skin.

### Typical Properties

#### As Supplied:

Appearance.....Black

Solids Content By Weight (ASTM D-2369).....10.6%(+/-1)

Solids Content By Volume (ASTM D2697).....10.4%(+/-1)

Weight Per Gallon (ASTM D1475).....8.4 lbs. (3.8 kg) (+/- .2)

Dry Time To Touch (ASTM D1640)..... 30 minutes @ 75°F (24°C)

Cure Time.....8+ hrs.

Volatile Organic Compounds.....90 grams/liter

Low & High Temperature Limits.....-30°F to 150°F (-34°C to 66°C)

### Packaging & Mixing

RP 1.1 Epoxy Primer is a single-component material available in 5-gallon (19 liter) pails. Stir material prior to application. RP 1.1 Epoxy Primer may be reduced with water for increased penetration over dense substrates. Shelf life in unopened containers is



*"It's What the Pros Use"*

## ***Technical Product Data***

---

one year from date of manufacture. Store at temperatures between 50°F and 100°F (10°C and 38°C). Do not open containers until ready to use the material.

*The information reported herein are based upon information reasonably available to Progressive Materials, LLC at the time publication, and are presented in good faith but are not to be construed as warranties or guarantees, expressed or implied.*