



Instructions - High Solids Silicone Roof Coating over RV, Camper and Mobile Homes

1 Preparation

A. Membrane Cleaning:

1. Sweep the roof to remove dirt, dust, and large debris.
2. In a large bucket, mix one part chlorine bleach with three parts water.
3. Use this solution and a stiff push broom and wash the entire roof surface to receive coating.
4. Use a hose to rinse the solution from the roof surface.
5. It is recommended that you power wash the roof surface if you have access to a power washer to remove any dirt and debris that was not removed by sweeping and scrubbing with the solution.

2 Silicone Coating Installation

- A. Ensure surface is completely dry.
- B. Install silicone coating in one pass over entire roof surface at a rate of 25 mils minimum. Application rate should be 2.0 gallons per 100 square feet.

3 Protection of Finished Work

- A. Ensure roof surface is free of traffic for minimum of 24 hours after silicone coating application or until coating is completely cured.